



High strength translucent, adhesive paste

Introduction

This is a specially formulated neutral cure silicone sealant specifically designed to meet the physical, chemical and temperature resistant requirements of MIL-A-46146B. It features exceptional physical properties and is compatible with many sensitive substrates including copper, brass, steel, aluminium and FR4, making this an ideal option for many electronic applications where high performance is paramount.

It is described as an Alkoxy 1-part room temperature vulcanising (RTV) silicone sealant. The Alkoxy cure system produces a silicone sealant with excellent adhesion to most common substrates

Key Features

- Meets the physical and chemical requirements of MIL A46146B
- High temperature resistance
- Non corrosive
- Adhesion to many substrates

Use and Cure Information

Typical Applications

- Assembly of electrical and electronic equipment
- Sealing and bonding of corrosion sensitive devices
- Shallow encapsulation of small circuits and connectors

Application and Cure

After removal of the package seal the product is ready for use. It can be applied manually or using a pneumatic caulking gun. Following exposure to atmospheric moisture the product begins to cure to a resilient, durable silicone elastomer. Full cure will depend on the relative humidity and ambient temperature. At 20 to 30°C and 40 to 70% Relative Humidity a 3mm section will normally cure in less than 24 hours.

The volatile by-products of the curing mechanism are relatively inoffensive alcohols.
(See Health and Safety Data)

Full bond strength and physical properties will be achieved in 7 days. Cure time depends on the thickness of sealant applied and the area exposed to the atmosphere.

It is recommended that a minimum thickness of 1 mm is achieved between parts to obtain best adhesion to substrates.

Property	Test Method	Value
Uncured Product		
Colour:		Transparent
Appearance:		Thixotropic paste
Tack Free Time:		45 minutes *
3mm Cure Through:		72 hours *
Extrusion Rate:		94 g / minute
* measured at 23+/-2°C and 65% relative humidity.		

Cured Elastomer

(after 7 days cure at 23+/-2°C and 65% relative humidity)

Tensile Strength:	BS903 Part A2	7.75 MPa
Elongation at Break :	BS903 Part A2	830 %
Tear Strength:	BS903 Part A3	42 kN/m
Hardness:	ASTM D 2240-95	35 ° Shore A
Specific Gravity:	BS 903 Part A1	1.16
Thermal Conductivity:		0.2 W/mK
Coefficient of Thermal Expansion:		
Volumetric		800 ppm / °C
Linear		267 ppm / °C
Min. Service Temperature:		662 °C
Max. Service Temperature:	AFS 1540B	316 °C

Electrical Properties

Volume Resistivity:	ASTM D-257	8.8E+14 9.cm
Dielectric Strength:	ASTM D-149	18 kV/mm
Dielectric Constant at 1MHz:	ASTM D-150	2.47
Dissipation Factor at 1MHz:	ASTM D-150	0.0035

Adhesion Testing

Adhesion to most substrates is possible with out the use of a primer but due to the high physical strength, the bond between substrate and silicone will be weaker than the cohesive strength of the silicone. To utilise the full potential of the product, it is recommended that Silcoset Primer is applied to substrates as detailed in the Technical Data Sheet. This will allow a strong covalent bond to form and result in an improved performance in adhesive strength.

Customers are advised to carry out their own tests on clean, degreased substrates to ensure satisfactory adhesion is achieved All values are typical and should not be accepted as a specification.

Packages – 90 ml and 310 ml cartridges, 20 kg pails

Storage and Shelf Life – Expected to be **12** months in 310 ml cartridges and 20 kg pails and 18 months in 90 ml tubes when stored in unopened containers below 40 °C.

Health and Safety – Material Safety Data Sheets available on request.

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

Toutes ces informations sont données en toute bonne foi mais sans garantie. Chaque application étant différente, il est vivement conseillé d'effectuer des tests préalables. Les spécifications concernant les propriétés sont données à titre indicatif et non comme étant spécifiques.